



GMS

GRAISSE MULTI SERVICES NLGI 2

CARACTERISTIQUES

- Based on polymers of superior synthesis, nature of lithium soap
- Smooth grease, adherent and stringy, green color
- Marine, totally immersible
- Insoluble in water, even salty, hot or cold
- Resistant to steam, acids, salt projections, detergents, weathering...
- High hydrodynamic lubricating power
- Superior protection in very severe use
- Extreme pressures
- Protects against corrosion
- Temperature resistance : -25°C to +140°C

APPLICATION

- Bearings
- Bare gears,
- Plain bearings,
- Saddles,
- Cardan joints,
- Slideways,
- Axes and joints,
- Ball guides,
- Threads,
- Mounting pins,
- Racks
- Chains...



CARACTERISTIQUES PHYSICO-CHIMIQUES

• Dropping point :	NFT 60-627	>190°C	
• Penetration worked 60 strokes	ISO 2137	1/10mm	265/295
• Loss after 10 000 strokes	ISO 2137	1/10mm	8
• Wheel Bearing 6h at 130°C	ASTM D1263	g	2,5
• Shell 4 balls welding	ASTM D2596	daN	> 315
• Shell 4 balls welding wear 1h 40kg	ASTM D266	mm	0,5
• Oxydation bombe Norma Hoffman after 100h	ASTM D942	kPa	< 50
• Anti-rust Emcor	NFR 60-135	Cotation	0
• Copper Blade 24h à 100°C	ASTM D4048	Cotation	<1b
• Torque at -25°C au démarrage	AIR 1650	mN.m	< 1000
• Torque at -25°C après 1h00	AIR 1650	mN.m	< 1000

CONDITIONNEMENT

- Tonnelet de 50kg

Code produit : IT1226022

STOCKAGE

- Keep away from light, heat and cold.

Cette fiche technique a été établie le 11/02/21 et annule toutes les fiches précédentes. Les renseignements fournis sont basés sur nos connaissances et expériences à ce jour. L'attention des utilisateurs attirée sur les risques éventuels encourus lorsque le produit est utilisé à d'autres usages que ceux pour lesquels il est conçu. Elle ne dispense en aucun cas l'utilisateur de connaître et d'appliquer l'ensemble des textes réglementant son activité. Il prendra sous sa seule responsabilité les précautions liées à l'utilisation qu'il fait du produit.